

Technical Data

HYBRIFLEX 480

General Purpose Building Sealant



Description

HYBRIFLEX 480 is a one part general purpose mid modulus building sealant based on hybrid polymer technology.

Benefits

- Will adhere to light damp surfaces
- May be used on trafficked floor joints (after suitable cure period) on joints less than 15mm wide
- Over paintable with common acrylic based paints (less so with alkyds)

Recommended For

Perimeter pointing of window/door frames. For expansion joints in brick, stone and concrete. Weather sealing applications. For parapet and roofline sealing. Weatherproofing sealing to most external applications. Construction and dilation joints where stress does not occur until fully cured. Trafficked floor joints less than 15mm wide.

Specification Compliances

HYBRIFLEX 480 may be used as a general purpose joint sealer for floors and walls and as a perimeter edge sealant in suitable glazing applications. HYBRIFLEX 480 is over paintable with suitable compatible paints. Preliminary test required before use.

Conforms to ISO 11600 Class F25HM and is CE Marked under EN15651 parts 1, façade and 4, pedestrian walkways under class F25HM and PW25HM.



Available in

380ml Cartridges in the following colours:

White
Grey

Storage

Store in cool, dry conditions between +5°C and +25°C. Storage outside these parameters will dramatically reduce shelf life.

Shelf Life

12 months from date of manufacture when stored as directed.

HYBRIFLEX 480

General Purpose Building Sealant

Health & Safety

Consult MSDS for full list of hazards.

Joint Dimensions

For maximum movement accommodation, it is recommended that:

1. The sealant joint depth should be no less than 5mm
2. Joint depth should be 5mm for joints up to 10mm wide
3. Joints above 10mm in width should be half the width in depth up to 20mm and minimum 10mm for wider joints

Joint depth may be adjusted to the correct size using EVERBUILD JOINT BACKER ROD or BOND BREAKING TAPE in cases where there is not enough depth to use Backer Rod.

Surface Preparation

All surfaces must be cleaned and be free from dust, grease and frost. Surfaces may be damp, but have no standing water. For most substrates, priming is not required, (except when area is intermittently or permanently immersed). Joints should be designed in accordance with BS6093. Square cross sections are preferred with a minimum 10mm depth.

NEW JOINTS: Concrete joints should be sawn, all debris flushed away after cutting and joints allowed to dry.

RENOVATING OLD JOINTS: Remove all old sealant from existing joint and clean back to sound concrete by wire brushing, grinding or shot blasting.

Specific Data

Sg	Approx 1.4g/cm ³
Cure Rate	Approx 2mm/24 hours
Solvent content;	Nil
Colour	White or grey
Workability	Good, and grooves remain after application
Viscosity: (HBDVII+/S70/10rpm)	Ca: 120,000-300,000cps (high)
Tack free	Ca. 60-90 mins at 23°C and 50% RH
Skin Formation time / 20°C/50% RH	20-35 mins
Movement accommodation:	+/-25%
Modulus at 100% elongation	0.75N/mm ²
Elongation at break	>200%
Tensile strength at break	0.9N/mm ²
Elastic Recovery (ISO7389)	74%
Hardness (shore A)	35-45 (1 week)
Chemical resistance (hypochlorite; dilute acid; dilute alkali; detergent; saline 2 weeks immersion)	Excellent
Humidity and water resistance	Excellent
Application temps	+5-+50°C
Temperature resistance	-50 to +150°C

Joint Width Calculation

Joint widths are calculated as in BS6213:

$$\text{Width} = \frac{M \times 100}{F} + M$$

Where M = movement and F = movement accommodation Factor

Primer

PVC/ Aluminium/ Glass: primer not normally necessary if desired use silicone primer N92.

Mortar: Primer with Sika Primer 3-N.

Coverage

Joint Size (mm)	Litre per metre run	Metres per 380ml Cartridge
5 x 5	0.025	15.20
5 x 10	0.050	7.60
10 x 10	0.100	3.80
15 x 10	0.150	1.90
20 x 10	0.200	1.27

Limitations

- Do not use on surfaces that bleed oils or plasticizers.
- Do not use in conjunction with bitumen or asphalt.
- Do not use in aquaria or as a mirror adhesive.
- Test compatibility with all substrates and paint systems prior to full scale use. May increase drying time of alkyd paints.
- Do not use in joints that are to be continually immersed.
- Do not use on Polypropylene, Polyethylene or Teflon.
- Use against natural stone: this product contains plasticizers which may cause some staining. Always check compatibility before use. If in doubt; Use Sika Primer 3N.
- Do not use for bedding double glazed units – use SILICONE 996 / 825.
- Yellowing can occur in predominantly dark conditions
- As quality of uPVC; ABS and most plastics varies dramatically, always carry out adhesion tests prior to full scale use. It is the user's responsibility to determine suitability for use. If in doubt, please contact Technical Services for advice.
- In areas of high UV some darkening/discoloration may occur. This does not affect the product performance.
- Yellowing can occur in predominantly dark places.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.