
PRIMER 100

Revision: 23/01/2012**Page 1 of 1****Technical Data:**

Base	Polyurethane
Consistency	Liquid
Curing System	Moisture cure and physical drying
Skin formation (20°C/65% R.H.)	Ca. 60 min.
Specific Gravity (DIN 53479)	1,03 g/ml
Flashpoint	24°C
Quantity to be applied	Ca. 5 m ² /l

Product:

Primer 100 is a universal primer based on polyurethane for porous surfaces.

Characteristics:

- Liquid, easy application
- Suitable for all professional sealants based on polyurethane

Applications:

Surfaces of expansion joints
Joint surfaces of porous materials with high water exposure

Packaging:

Colour: transparent
Packaging: alu bottle 500ml

Shelflife:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°. Protect against frost!

Surfaces:

Type: all porous surfaces
State of Surface: clean, dry, free of dust and grease
We recommend a preliminary compatibility test.

Application:

Method: brush
Application temperature: +5°C to +25°C
Clean: with white spirit immediately after application
Recommendation: after application of Primer 100, wait 60 minutes at least and 4 hours at the most before applying a sealant

Health- and Safety Recommendation:

Apply the usual industrial hygiene.
Wear gloves and goggles.

Remarks:

If the maximum waiting time of 4 hours has passed before application of the sealant, apply a new layer of Primer 100.

If the product is stored at higher temperatures (> 25°C), it is possible that the product becomes unusable before the due date.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.